

ComfortHush™

ComfortHush™ is a range of locally produced acoustic performance laminates incorporating a special 3 ply acoustic PVB interlayer designed to reduce sound transmission and also features a Low E coated component to provide improved thermal insulation performance. ComfortHush™ is a Grade A laminated Safety Glass.

Features



Noise Control

The 3-layered acoustic interlayer laminate is specially designed to dampen noise and limit vibrations.



Energy Efficiency

ComfortHush™ can keep the temperature of your room controlled, lowering your energy consumption and reducing the need for additional heating and cooling.



Low E Coating

Coating is applied that allows natural light through without emitting radiant heat, maximising light and energy efficiency.



Laminated

The ComfortHush™ range has a laminated layer that contributes towards making the range a Grade A safety glass as standard.



Safety & Security

Our Products have been tested to Grade A safety glass protection.



UV Protection

The PVB interlayer used in ComfortHush™ eliminates 99% of ultraviolet radiation.



Range of Tones

Colour options are available within the ComfortHush™ range.



Climate

ComfortHush™ is designed with a consideration for mixed and warmer climates or where mid-range solar control and insulation are desired.

Product Range

Clear

Available Thickness (mm)	6.5, 10.5
Maximum Sheet Size (mm)	5100×3210 (6.5mm), 3660×2440 (10.5mm)

Neutral

Available Thickness (mm)	6.5, 10.5
Maximum Sheet Size (mm)	3660×2440

Grey

Available Thickness (mm)	6.88, 10.88
Maximum Sheet Size (mm)	3660×2440

Translucent

Available Thickness (mm)	6.88
Maximum Sheet Size (mm)	3660×2440

Applications

External

Doors, Windows, Shop Front

Technical Data

Performance

Single Glazing

Product Name	Nominal Thickness	Visible		Solar		UV Trans.	U-Value	SHGC	Shading Co.	Weight m ²	
		Trans.	Refl. Out	Refl. In	Trans.						
ComfortHush™ Clear (#4)	6.5	81	11	11	62	9	<1	3.6	0.67	0.77	15.5
ComfortHush™ Clear (#4)	10.5	80	10	11	57	8	<1	3.6	0.64	0.74	25.5
ComfortHush™ Neutral (#4)	6.5	60	8	10	42	7	<1	3.6	0.52	0.59	15.5
ComfortHush™ Neutral (#4)	10.5	59	8	10	39	7	<1	3.6	0.49	0.57	25.5
ComfortHush™ Grey (#4)	6.88	41	6	9	39	6	<1	3.6	0.5	0.58	15.9
ComfortHush™ Grey (#4)	10.88	40	6	9	36	6	<1	3.5	0.48	0.55	25.9
ComfortHush™ Translucent (#4)	6.88	62	8	10	48	7	<1	3.6	0.57	0.65	15.9

Double Glazing

Product Name	Nominal Thickness	Visible		Solar		UV Trans.	U-Value	SHGC	Shading Co.	Weight m ²		
		Trans.	Refl. Out	Refl. In	Trans.							
ComfortHush™ Clear (#4) + QFloat™ Clear	6.5+12+6	72	16	17	50	12	<1	1.9	1.6	0.59	0.68	30.5
ComfortHush™ Clear (#4) + QFloat™ Clear	10.5+12+6	71	15	17	46	11	<1	1.9	1.6	0.55	0.64	40.5
ComfortHush™ Neutral (#4) + QFloat™ Clear	6.5+12+5	53	11	16	34	9	<1	1.9	1.6	0.43	0.49	30.5
ComfortHush™ Neutral (#4) + QFloat™ Clear	10.5+12+6	53	11	16	31	8	<1	1.9	1.6	0.4	0.46	40.5
ComfortHush™ Grey (#4) + QFloat™ Clear	6.88+12+6	36	7	15	31	8	<1	1.9	1.6	0.41	0.47	30.9
ComfortHush™ Grey (#4) + QFloat™ Clear	10.88+12+6	36	7	15	28	7	<1	1.9	1.6	0.38	0.44	40.9
ComfortHush™ Translucent (#4) + QFloat™ Clear	6.88+12+6	55	11	16	38	9	<1	1.9	1.6	0.48	0.55	30.9
(#4) + QFloat™ Clear	+12+6	54	11	16	36	8	<1	1.9	1.6	0.45	0.52	40.9

Considerations

Acoustic Control

To avoid noise leaks, you need to ensure that ComfortHush™ is installed in a frame that's well-sealed and professionally fitted. If the frame isn't sealed properly then ComfortHush™ can't work to its full potential.

Glazing

ComfortHush when single glazed, must be glazed with the exposed coating to the inside of the building (surface #4).

Glass

Under certain light conditions, a haze effect can be seen in the glass.

Glass Processing

Exposed edges should be protected from moisture ingress.

Large Projects

Oceania Glass recommends that for large glazing facades (particularly curtain wall) the customer should highlight this in writing to enable consideration of colour management of supplied product.

How to Specify

Available colours and thicknesses:

Clear	6.5 & 10.5mm
Neutral	6.5 & 10.5mm
Grey	6.88 & 10.88mm
Translucent	6.88mm

ComfortHush™ Acoustic Data

Single Glazing

Thickness (mm)	Rw
6.5	36
6.88	36
10.5	38
10.88	38
12.5	40

Insulated Glass Unit

Make up	Rw
4/12/6.5	37
6/12/6.5	39
6/16/6.5	41
8/12/6.5	42
8/12/8.5	43
10/12/8.5	44
10/12/12.5	46

Select from: Laminated.

If unsure, select in compliance with AS1288-2021 or manufacturers recommendation.

The glass shall comply with the following performance criteria:

- U value
- Solar Heat Gain Coefficient (SHGC)
- Visible Light Transmission %
- Glass Only Values
- Total window

Toned Glass

Toned glass absorbs a proportion of solar radiation and may require a thermal assessment depending on application.

All glass is to be selected and installed in accordance but not exclusively with the following Australian and/or New Zealand Standards

- AS 1288 Glass in Buildings Selection and Installation
- AS 1170 Minimum Wind Loads on Structures
- AS/NZ 2208 Safety Glazing Materials in Buildings
- AS/NZ 4666 Insulating Glass Units
- AS/NZ 4667 Quality Requirements for cut-to-size and Processed Glass

Oceania Glass makes and distributes glass. Oceania Glass does not process glass nor produce Insulated Glass Units. Processing of glass and production of Insulated Glass Units is undertaken by independent processors. Speak with your nominated glass processors to understand their processing capability.